



**Summary of Substantive Changes
between the 2012a and the 2012ae1 editions of
ASTM D2513, “Polyethylene (PE) Gas Pressure Pipe, Tubing, and Fittings”**

Presented to the IAPMO Standards Review Committee on February 11, 2013

General: The change to this standard is editorial and should not have an impact on currently listed products. The editorial change is:

- Corrected the text from 1 to 1h (see Section 6.3)

Section 6.3, Conditioning: Editorially clarified that the minimum conditioning time in water is 1 hour, as follows:

For those tests where conditioning is required or unless otherwise specified, condition the specimens prior to testing for a minimum of 1h in water or 4h in air at $73.4 \pm 3.6^{\circ}\text{F}$ ($23 \pm 2^{\circ}\text{C}$).