



**Summary of Substantive Changes
between the 2006 and the 2012 editions of
ASTM D1785 “Poly(Vinyl Chloride) (PVC) Plastic Pipe,
Schedules 40, 80, and 120”**

Presented to the IAPMO Standards Review Committee on July 9, 2012

General: The changes to this standard should not have an impact on currently listed products. The changes are:

- the relative humidity tolerance was increased from ~~±5%~~ to ±10% (Section 8.1 and 8.2)

Section 8.1, Conditioning:

Condition the test specimens at $73.4 \pm 3.6^{\circ}\text{F}$ ($23 \pm 2^{\circ}\text{C}$) and 50 ~~±5%~~ ±10% relative humidity for not less than 40 h prior to test in accordance with Procedure A of Practice D618, for those tests where conditioning is required.

Section 8.2, Test Conditions:

Conduct tests in the standard laboratory atmosphere of $73.4 \pm 3.6^{\circ}\text{F}$ ($23 \pm 2^{\circ}\text{C}$) and 50 ~~±5%~~ ±10% relative humidity, unless otherwise specified in the test methods or in this specification.