



**Summary of Substantive Changes
between the 2006b^{e1} and the 2012 editions of
ASTM F480, “Thermoplastic Well Casing Pipe and Couplings Made in
Standard Dimension Ratios (SDR), SCH 40 and SCH 80”**

Presented to the IAPMO Standards Review Committee on October 8, 2012

General: The changes to this standard should not have an impact on currently listed products. The changes are:

- Increased the relative humidity tolerance for conditioning the specimens prior to testing (Section 7.2)

Section 7.2, Conditioning: The allowable variation in relative humidity was increased as follows:
Unless otherwise specified, condition the specimens prior to test at $72.4 \pm 3.6^{\circ}\text{F}$ ($23 \pm 2^{\circ}\text{C}$) and $50 \pm 5\%$ ~~10%~~ relative humidity for not less than 40 h in accordance with Procedure A of Practice D618. The manufacturer may use shorter conditioning time, but in case of disagreement Procedure A of Practice D618 shall be used.