



**Summary of Substantive Changes
between the 2017 and the 2021 editions of
ASTM D2466 “Poly(Vinyl Chloride) (PVC) Plastic Pipe Fittings, Schedule 40”**

Presented to the IAPMO Standards Review Committee on November 15, 2021

General: The changes to this standard should not have an impact on currently listed products. The substantive changes are:

- Revised temperature tolerance requirements for test conditioning (see Section 8.1 and 8.2)

8. Test Methods

8.1 Conditioning—Condition the test specimens at $73^{\circ}\text{F} \pm 3.64^{\circ}\text{F}$ ($23^{\circ}\text{C} \pm 2^{\circ}\text{C}$) and $50 \pm 10\%$ relative humidity for not less than 40 h prior to test in accordance with Procedure A of Practice D618, for those tests where conditioning is required.

8.2 Test Conditions—Conduct tests in the Standard Laboratory Atmosphere of $73^{\circ}\text{F} \pm 3.64^{\circ}\text{F}$ ($23^{\circ}\text{C} \pm 2^{\circ}\text{C}$) and $50\% \pm 10\%$ relative humidity, unless otherwise specified in the test methods or in this specification.